

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification ⁵ : G02F 1/155, 1/153	A1	(11) International Publication Number: WO 92/18896 (43) International Publication Date: 29 October 1992 (29.10.92)
---	-----------	--

(21) International Application Number: PCT/US92/02634

(22) International Filing Date: 30 March 1992 (30.03.92)

(30) Priority data:
686,637 17 April 1991 (17.04.91) US(71) Applicant: MARTIN MARIETTA CORPORATION [US/
US]; 6801 Rockledge Drive, Bethesda, MD 20817 (US).(72) Inventors: TADROS, Maher, Ebeid ; 10047 Moss Gate
Court, Ellicott City, MD 21043 (US). MASON, James,
Anthony ; 6310 Pine Drive, Huntington, WV 25705 (US).
KADOCH, Christopher Allen ; 12007 Alta Carmel
Court, Apartment No. 325, San Diego, CA 92128 (US).(74) Agents: WINCHELL, Bruce, M. et al.; Martin Marietta
Corporation, 6801 Rockledge Drive, Bethesda, MD
20817 (US).(81) Designated States: AT (European patent), BE (European
patent), CA, CH (European patent), DE (European pa-
tent), DK (European patent), ES (European patent), FR
(European patent), GB (European patent), GR (Euro-
pean patent), IT (European patent), JP, LU (European
patent), MC (European patent), NL (European patent),
SE (European patent).**Published***With international search report.
Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.*

(54) Title: IMPROVED ELECTRODE FOR DISPLAY DEVICES



(57) Abstract

An improved working electrode for use in display devices is disclosed. The working electrode comprises a transparent metal grid (11a, 11b, 11c) having a coating of metal oxide (12) thereon. Suitable metal grids include Cu, Au, Ag, Al, Pt, Ni and Zn, while suitable metal oxide coatings include In₂O₃, SnO₂ and indium tin oxide (ITO). The display devices preferably include an electrochromic material (15) comprising an aqueous solution of an electro-chemically depositable metal. Display devices in which the present working electrode is used possess favorable characteristics such as rapid response times, wide dynamic range, high transmittance and improved uniformity. The devices are particularly suitable for large surface area applications.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	ML	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TC	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

IMPROVED ELECTRODE FOR DISPLAY DEVICES

FIELD OF THE INVENTION

The present invention relates to display devices. More particularly, the invention relates to an improved working electrode
5 for use in display devices which provides rapid response times, wide dynamic range, high transmittance and improved uniformity. The devices are particularly suitable for large area applications.

BACKGROUND OF THE INVENTION

Numerous processes are known for the modulation of visible
10 light. Among these processes, electrochromic techniques use the reversible change of color and/or optical density obtained by an electrochemical redox reaction of an electrochromic material in which the oxidized form and reduced form are of different colors and/or different optical densities.

15 Electrochromic materials change their optical properties due to the action of an electric field and can be changed back to the original state by a field reversal. In most electrochromic materials, the mechanism underlying the optical change is the insertion of ions into the electrochromic material and the subsequent
20 extraction of the same ions. The devices can show open circuit memory, i.e., voltage has to be applied only when the optical properties are to be altered. Most electrochromic devices require an ion-containing material (electrolyte) in proximity with the electrochromic layer as well as transparent layers for setting up a
25 distributed electric field.

- 2 -

Recently it has become evident that electrochromism occurs in numerous transition metal oxides and organic materials [See C.M. Lampert and C.G. Granqvist, "Introduction to Chromogenics", Large-Area Chromogenics: Materials and Devices for Transmittance Control, SPIE Institute Series Vol. IS 4, pp 2-19 (1990)].

Many applications exist for electrochromic materials including display panels, variable transmittance windows and variable reflectance mirrors. Prior art electrochromic materials include metal oxides such as WO_3 , MO_3 , V_2O_5 , Ir_2O_3 and Nb_2O_5 , polymers such as polyaniline, polyacetylene, polypyrrole and polythiophene, and aqueous solutions of metal ions such as Zn.

U.S. Patent No. 4,009,936 issued March 1, 1977 to Kasai discloses electrochromic display devices including a solid electrochromic material and a solid electrolyte. The electrochromic material is selected from tungsten oxide, molybdenum oxide, titanium oxide, vanadium oxide, cobalt tungstate, tin oxide, tellurium oxide, iron oxide, rare earth oxides, metal halides, strontium titanate, metal carbonyls, salicylidene aniline, and organic materials containing a hydrazone group, an osazone group, a semicarbazone group or a sydnone group. The electrolyte is selected from $Ag_7I_4PO_4$, AgI, and AgI in combination with a member of the $Ag_4P_2O_7$ series, the Ag_2WO_4 series, the RbI series, the NH_4I series, the KCN series, or the $C_4H_8SCH_3I$ series. The display devices also include a transparent electrode in contact with the electrochromic material comprising a conductive film of unspecified composition coated on a glass substrate. The devices are said to be useful for display purposes, e.g., timepieces and the like.

U.S. Patent No. 4,448,493 issued May 15, 1984 to Matsudaira et al discloses electrochromic display devices including an electrochromic layer and a solid proton conductive layer. The electrochromic layer

consists of a transition metal oxide such as WO_3 , MoO_3 , TiO_2 , Ir_2O_3 , Rh_2O_3 , NiO or V_2O_5 . The proton conductive layer comprises a mixture of acids selected from titanitic, stannic, antimonitic, zirconic, niobic, tantalitic and silicic acid. The display devices also include a transparent electrode contacting the electrochromic material and comprising a thin film of indium oxide (In_2O_3) or tin oxide (SnO_2) deposited on a transparent substrate such as glass or synthetic resin. The disclosed devices are said to possess shortened response times, with speeds on the order of 1 to 10 seconds being exemplary.

U.S. Patent No. 4,459,035 issued July 10, 1984 to Nanya et al discloses electrochromic display devices including a reduction electrochromic material and an oxidation electrochromic material separated by an ion permeable insulating layer. The reduction electrochromic material is WO_3 or MoO_3 , while the oxidation electrochromic material is iridium hydroxide $[Ir(OH)_n]$, rhodium hydroxide $[Rh(OH)_n]$ or nickel hydroxide $[Ni(OH)_n]$. As the ion permeable insulator, Ta_2O_5 , Cr_2O_3 or SiO_2 may be used. The display devices also include a transparent electrode contacting the reduction electrochromic material and a counter electrode contacting the oxidation electrochromic material. During operation of the device, the oxidation electrochromic material is said to function as an acceptor of protons, thereby preventing evolution of hydrogen gas on the surface of the counter electrode. The devices may be used as display panels for electronic timepieces.

U.S. Patent No. 4,233,339 issued November 11, 1980 to Leibowitz et al discloses electrochromic display devices including an electrochromic material and an electrolyte. The electrochromic material may comprise WO_3 which has been partially converted from the amorphous to the crystalline form which is said to significantly increase the etch resistance of the material, thereby increasing the useful life of the device. The electrolyte may be liquid, gel, paste or solid. The display devices also include a transparent electrode

in contact with the electrochromic material comprising a conductive layer, such as tin oxide, deposited on a transparent glass or plastic substrate.

Japanese Patent No. 56-109317 to Nagasawa et al, published
5 August 29, 1981, discloses electrochromic display devices having a layer of amorphous WO_3 and a layer of crystalline WO_3 separated from each other by an ion conductive layer such as SiO_2 , Al_2O_3 , ZrO_2 , MgF_2 or CaF_2 . The devices also include a transparent electrode in contact with each of the WO_3 layers
10 comprising tin oxide, indium oxide or indium tin oxide (ITO). The crystalline WO_3 is said to maintain a coulomb balance within the devices and to produce long life and high reliability.

U.S. Patent No. 4,135,790 issued January 23, 1979 to Takahashi et al discloses electrochromic elements comprising a thin layer of
15 electrochromic material and a thin layer of electron blocking material sandwiched between a pair of transparent electrodes to form a unit cell. Multiple unit cells are stacked together to form a multi-layer structure. The electrochromic material may be WO_3 or MoO_3 . The use of multiple thin layers of electrochromic
20 material is said to reduce the response times of the devices.

U.S. Patent No. 4,768,865 issued September 6, 1988 to Greenberg et al discloses transparent electrochromic windows using WO_3 as the electrochromic material along with a layer of ion conductive material. A counter electrode in the form of a metal grid is placed
25 in contact with the ion conductive material. The metal grid participates in a balancing half-cell reaction whereby the metal grid is oxidized or reduced in response to the electrochromic transition of the WO_3 . Use of the metal grid is said to allow operation of the device at lower potentials which prevents electrolysis of
30 water and concurrent gas evolution. The devices have a response time on the order of two minutes. Similar devices are disclosed by

Kuo-Chuan Ho, David E. Singleton and Charles B. Greenberg in an article: "Effect of Cell Size on the Performance of Electrochromic Windows," Proceedings of the Symposium on Electrochromic Materials, Proceedings - The Electrochemical Society, Vol. 90, No. 2 pp. 349-364
5 (1989).

U.S. Patent No. 4,887,890 issued December 19, 1989 to Scherber et al discloses transparent electrochromic panes or foils including an electrochromic polymer layer and an electrolyte layer sandwiched between two transparent electrodes. Suitable polymers include
10 polyaniline, poly-O-phenyldiamine, polyaniline-3-sulfonic acid, polypyrrol and polythiophene, while suitable electrolytes include polymeric sulfonic acid, polymeric carbonic acid, buffered H_2SO_4 , buffered $HClO_4$ and HCl . Suitable transparent electrodes include In_2O_3/SnO_2 (ITO), SnO_2 , In_2O_3 , Mo, Pd,
15 Pt, Rh, Ti and ZnSe which may be coated on a glass pane or foil. The devices are said to have response times on the order of a few seconds.

U.S. Patent No. 4,749,260 issued June 7, 1988 to Yang et al discloses transparent electrochromic display devices including a
20 layer of polyaniline electrochromic material and a layer of electrolyte material disposed between two transparent electrodes. The electrodes comprise a transparent conductive coating such as SnO_2 , In_2O_3 , Pt or Au deposited on a glass or plastic sheet. The devices may employ multiple layers of electrochromic materials to
25 produce tint and color changes.

U.S. Patent No. 4,550,982 issued November 5, 1985 to Hirai discloses electrochromic display devices including a layer of electrochromic material and a layer of electrolyte material disposed between two transparent electrodes. The electrochromic material
30 consists of a polymer film comprising at least one organic electrochromic material and at least one ionic material wherein the ionic material is capable of exchanging ions with the organic electrochromic material to serve as an ion donor or acceptor.

Suitable electrodes include SnO_2 or ITO coated on a glass or plastic plate. The devices possess a response time on the order of 0.5 to 6 seconds.

In an article by Richard M. Bendert and Dennis A. Corrigan
5 entitled: "Effect of Coprecipitated Metal Ions on the Electrochromic
Properties of Nickel Hydroxide," J. Electrochem. Soc., Vol. 136, No.
5, May 1989, pp. 1369-1374, electrochromic films are disclosed
comprising nickel hydroxide alone and in combination with minor
amounts of other metal hydroxides. The films are said to possess
10 high coloration efficiency throughout the visible region and to be
useful in window applications.

U.S. Patent No. 4,263,105 issued April 21, 1981 to Robillard et
al discloses electrosensitive recording materials having an
electrosensitive layer comprising a bismuth or antimony salt and a
15 semiconductor oxide pigment, such as TiO_2 , ZnO , SnO_2 or
 Al_2O_3 , dispersed in a binder. The electrosensitive layer is
deposited on a conductive layer, such as a metal foil, which in turn
is laminated on a paper sheet or plastic film substrate. Permanent
recordings may be formed by contacting the electrosensitive layer
20 with a writing electrode.

U.S. Patent No. 4,596,635 issued June 24, 1986 to Warszawski
discloses recording media comprising an electrosensitive layer coated
on a substrate such as paper or plastic film. The electrosensitive
layer comprises a homogeneous aqueous solution of a hydrosoluble salt
25 of a cathodically depositable metal and a hydrosoluble polymer
resin. Suitable electrodepositable metals are said to be Zn, Cd, Pb,
Ag, Cu, Fe, Ni, Co, Sn, In, Pt, Pd, Au, Bi, Sb, Te, Se, Mn, Tl, Ga,
As, Hg and Cr. Suitable polymer resins include hydroxyethylcellulose
and carboxymethylcellulose. Permanent recordings may be produced by
30 contacting the electrosensitive layer with a writing electrode.

European Patent Application Publication No. 0300919 of
Warszawski, published January 25, 1989, which is hereby incorporated
by reference, discloses electrochromic display devices comprising an
electrolytic material disposed between two electrodes. The
5 electrolytic material comprises a water soluble salt of a
cathodically depositable metal and a watersoluble polymer resin.
Suitable cathodically depositable metals are said to include Zn, Cd,
Pb, Ag, Cu, Fe, Co, Ni, Sn, In, Pt, Pd, Au, Bi, Sb, Te, Mn, Ti, Se,
Ga, As, Hg, Cr, W and Mo, while suitable polymer resins include
10 hydroxyethylcellulose, polyvinyl alcohol and polyvinylpyrrolidone.
The electrodes comprise a first transparent working electrode and a
second counter electrode which may, or may not, be transparent,
depending on the desired application. The working electrode may
comprise a thin layer of gold, tin oxide, indium oxide or ITO
15 deposited on a glass or plastic substrate, while the counter
electrode may comprise a flexible graphite sheet, a plastic material
filled with particles of carbon or metal, or a glass or plastic sheet
coated with a thin layer of semiconductor oxide. The disclosed
devices are useful for the display of alphanumeric, graphic and other
20 visual information.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a new working
electrode for use in display devices.

Another object of the present invention is to provide an improved
25 working electrode for large area display devices, the electrode
comprising a metal grid having a metal oxide coating thereon.

Another object of the present invention is to provide an improved
display device which is characterized by rapid response times, wide
dynamic range, high transmittance and improved uniformity. The
30 devices are particularly suited for large area applications.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic side cross-sectional view of a display device according to the present invention.

Figure 2 is a topographical view of a metal grid used in a
5 working electrode of the present invention.

Figure 3 is a graph showing the effect of an electric field reversal on the percent reflectance of a display device of the present invention at varying wavelengths.

DETAILED DESCRIPTION OF THE INVENTION

10 In accordance with the present invention, a display device is provided comprising a working electrode, a counter electrode, and an electrochromic material disposed therebetween.

The working electrode comprises an electrically conductive metal grid or bus having a coating of metal oxide thereon. The metal grid
15 and coating are preferably disposed on a transparent substrate which serves to provide structural integrity. Figure 1 illustrates a cross section of a display device in accordance with one embodiment of the present invention. Metal grid 11a, 11b and 11c (shown in cross section) is coated with a metal oxide layer 12. A substrate 13
20 serves to support the metal grid 11a, 11b and 11c and metal oxide layer 12. A counter electrode 14 is provided in contact with an electrochromic material 15 which in turn is in contact with the metal oxide layer 12. Electrical contacts (not shown) may be connected in a conventional manner to the working electrode 11a, 11b and 11c and
25 counter electrode 14. It is noted that the elements illustrated in Figure 1 are not to scale.

The metal grid is chosen such that it does not substantially reduce transparency while insuring uniform rapid charge distribution over a large surface area. The grid may be made of any suitable metal, preferably metals having high electrical conductivity.

5 Suitable metals include Cu, Au, Ag, Al, Zn, Ni and Pt, with Au being a preferred metal due to its high conductivity and chemical inertness. The metal grid may be patterned in any desired geometry, such as square, rectangular, hexagonal, circular, parallel lines, etc. Figure 2 shows a preferred metal pattern in which a square grid
10 is surrounded by a relatively thick bus. The bus is used to facilitate electrical connection to the grid and to increase speed during operation of the display device. While the description provided in the present disclosure focuses on the use of a square grid geometry, it should be recognized that other configurations are
15 also within the scope of the present invention. In the typical grid pattern, line widths of from about 5 to about 200 microns may be used, with widths of about 20 microns being preferred. Line spacings of from about 100 to about 2000 microns may be employed, with
20 spacings of about 500 microns being preferred. Line heights of from about 0.1 to about 100 microns are suitable, with heights of from about 0.2 to about 3 microns being preferred. In order to provide sufficient transparency, the lines of the grid should cover less than 50 percent of the surface area, preferably less than about 25
25 percent, more preferably less than about 10 percent and most preferably less than about 5 percent of the surface. However, the lines should be of sufficient size and spacing to permit a uniform rapid charge distribution over the surface of the electrode. The electrical resistivity of the metal grid may range from about 0.02 to about 3 ohms per square, with about 0.4 ohms per square being
30 preferred. For purposes of the present invention the term "ohms per square" is used to designate sheet resistivity over a given surface area in a manner conventional in the conductive coatings art.

The metal grid is preferably formed on a substrate by such conventional methods as sputtering, chemical vapor deposition (CVD),
35 and the like. The substrate provides structural integrity to the

metal grid and is chosen such that it is transparent in the desired spectral region. The substrate may be glass, such as soda glass or borosilicate glass, may be a polymer, such as polyethylene, polytetrafluoroethylene (Teflon) or polyester (Mylar), or may be a transparent crystalline material, such as ZnS or ZnSe. In uses where durability or flexibility is desired, polymer substrates may be preferred.

The working electrode of the present invention also comprises an electrically conductive metal oxide coating over the metal grid. The metal oxide coating prevents unwanted reactions between the grid and the electrochromic material and also provides improved characteristics, such as uniformity and wide dynamic range.

The metal oxide coating is selected such that it is electrically conductive and transparent. Suitable metal oxides include indium oxide (In_2O_3), tin oxide (SnO_2), indium tin oxide (ITO), zinc oxide (ZnO) and cadmium stannate, with indium tin oxide being the most preferred. The metal oxide is doped with minor amounts of constituents such as fluorine, antimony, aluminum, etc. in a known manner to achieve sufficient electrical conductivity. The metal oxide coating may preferably range in thickness from about 50 to about 2000 Angstroms, with a thickness of about 1000 Angstroms, being most preferred. The electrical resistivity of the metal oxide coating may preferably range from about 10 to about 10,000 ohms per square, with lower resistivity being preferred for increased speed. Resistivities of from about 100 to about 200 ohms per square have been found to be particularly advantageous.

As the counter electrode, any suitable electrically conductive material may be used. For example, the counter electrode may comprise a metal such as Cu, Au, Pb, Sn, Zn or stainless steel. The metal may be provided in the form of a relatively thick sheet sufficient to provide structural support for the device. Alternatively, the metal may be provided as a thin coating on a substrate such as a conventional circuit board. The counter

electrode may also comprise carbon, e.g., in the form of a graphite sheet, or a polymer impregnated with metal or carbon particles. The counter electrode may be rigid or flexible depending upon the application sought. In addition, the counter electrode may be opaque
5 or transparent, depending upon the use of the device. If transparency is desired, the counter electrode may comprise a metal grid or thin layer of electrically conductive material.

As the electrochromic material, several types of materials may be used, with the most preferred comprising an aqueous solution of an
10 electrochemically depositable metal. Alternative electrochromic materials include polymers such as polyaniline, polyacetylene, polypyrrole and polythiophene, metal oxides such as WO_3 , MoO_3 and $\text{Ni}(\text{OH})_2$, and Prussian blue. Each of these alternative materials is used in conjunction with another electrolyte layer in a known manner
15 to achieve the electrochromic effect. While the present disclosure focuses on electrochromic materials comprising aqueous solutions of electrochemically depositable metals, it should be recognized that other types of electrochromic materials are within the scope of the present invention.

20 The preferred electrolytic material according to the present invention comprises a mixture of at least one water soluble salt of a metal that is cathodically depositable from an aqueous solution of its simple or complex ions, at least one polymeric resin preferably in the ratio of one part by weight for 0.05 to 50 parts of anhydrous
25 salt, and water. In addition, the electrolytic material may comprise additional redox couples, nonelectrochemically depositable metals, pigments, acids, reticulation agents, complexing agents and forming or application agents.

30 The water soluble salt may comprise a metal selected from zinc, cadmium, lead, silver, copper, iron, cobalt, nickel, tin, indium, platinum, palladium, gold, bismuth, antimony, tellurium, manganese, thallium, selenium, gallium, arsenic, mercury, chromium, tungsten, molybdenum and combinations thereof. Preferred metals include zinc, nickel and cobalt.

The metallic salts usable in this invention are ionic complexing where the metal is present in the form of a cation or incorporated in a cationic complex. The pH of these compositions is chosen such that the compositions become substantially completely soluble in an aqueous medium. Suitable anions include chloride, nitrate, sulfate, borate, fluoride, iodide, bromide, fluoroboride, fluorosilicate, fluorogallate, dihydrogenophosphate, chlorate, perchlorate, bromate, selenate, thiosulfate, thiocyanate, formate, acetate, butyrate, hexanoate, adipate, citrate, lactate, oleate, oxalate, propionate, salicylate, glycinate, glycollate, glycerophosphate, tartrate, acetyl-acetate, isopropylate, benzoate, malate, benzene sulfonate and 1 phenol-4 sulfonate. It is found to be particularly advantageous to have halogen anions (chloride, bromide, iodide, fluoride) in the electrolytic material.

The polymeric resins used comprise resins capable of forming aqueous solutions and also resins capable of forming colloidal dispersions in water. Exemplary polymers include polyvinylpyrrolidone, polyvinyl alcohol, poly-2-acrylamido-2-methylpropane sulfonic acid and hydroxyethylcellulose. The polymeric resin preferably confers to the material a viscosity which facilitates application in thin layers.

Water is preferably present in a maximum amount such that the electrolytic material retains a solid consistency in the absence of external constraints. Water should be provided in a minimum amount such that a sufficient ratio of water to the water soluble salt is achieved.

At least one solid can be dispersed in a homogenous manner in the electrolytic material particularly to improve or modify the mechanical properties, the appearance of the device, and the diffusion and reflection of light. In particular one such solid is a pigment which masks the counter electrode to provide a background offering the most desirable contrast or color. Numerous mineral and organic pigments, both white and colored, can be used as long as they

do not substantially interact chemically with the other constituents of the electrolytic material. A preferred white pigment in most electrolytic media according to the present invention and possessing great covering power as well as a high index of whiteness is titanium dioxide principally in the form of rutile and anatase crystals. The pigment can be used in association with a colored pigment either as a mixture or in superposition in a composite layer of electrolytic material which permits modification of the color saturation and/or for a background color improvement in the high covering power of the titanium dioxide. Such colored pigments are for example zinc chromate, cobalt blue and chrome oxide. One can likewise mix titanium oxide and a soluble colorant. Numerous colorants, particularly the type used for watercolor paintings, are usable with the reservation that they must not interact chemically with the other constituents of the electrolytic material.

The electrolytic material of the present invention is produced by dissolution of the water soluble constituents and dispersion of the nonsoluble constituents in water followed by evaporation of a part of this water or, in contrast, dissolution by an addition of water up to the point of obtaining a suitable viscosity. One characteristic of this mode of fabrication of the electrolytic material is to permit adjustment of the viscosity of the electrolytic material between limits of a liquid approaching water to that of a solid paste. One can thus adjust the viscosity for the chosen mode of application of the electrolytic material. Application may be achieved by, for example, xerography, air layer, bar wire, scraping, extrusion, dipping, tape casting or any other suitable technique for forming a thin film of the material.

The electrolytic material is applied to one or more of the electrodes in a thin layer. The material is then dried (by hot air, infrared, exposure to the surrounding atmosphere, etc.) up to the point of obtaining material of solid consistency in the final composition. It can also be subjected eventually to an additional

- 14 -

treatment for example a thermal treatment to obtain accelerated reticulation of the resin. Thicknesses of the electrolytic material may range from less than 1 to greater than 1000 microns with 100 to 200 microns being preferred.

5 The electrolytic material can be coated or applied to an electrode in a single layer or in many layers consecutively with intermediate or simultaneous drying. The different layers can be of identical composition or may comprise different percentages of total constituents. One may thus obtain a layer of electrolytic material
10 of composite structure.

In order to retain sufficient water content in the electrolytic material, a seal is preferably used between the working electrode and counter electrode. The seal may comprise an adhesive, such as epoxy, and is selected such that it has a sufficiently low permeability to
15 water to prevent unwanted drying of the electrolytic material. Where polymeric substrates are used in the working electrode, care should be taken that the polymer has low water permeability. Sealants may be applied to the substrate in order to prevent drying.

Display devices incorporating the above described electrolytic
20 material, and using the working electrode of the present invention comprising a metal grid having a metal oxide coating thereon, have been found to possess highly advantageous characteristics. It has been found that the metal oxide coating provides for substantially uniform deposition of metal ions from the electrolytic material
25 during operation of the device. The metal oxide coating allows for metal deposition over the entire surface of the working electrode, which prevents transmittance of light through the working electrode during operation. Absent the metal oxide coating, the metal ions contained within the electrolytic material do not deposit uniformly
30 over the entire electrode surface. Instead, the metal ions deposit directly on the metal grid, leaving the areas between the grid lines uncoated, which allows light to pass through the electrode during

- 15 -

operation. The metal oxide coating of the present invention is therefore essential to the operation of the disclosed display devices.

Figure 3 graphically shows reflectance characteristics over
5 varying wavelengths for a typical display device in accordance with the present invention. When an electric field is applied to the working electrode acting as an anode, the device turns white, as evidenced by the high reflectivity of well over 50 percent and typically over 70 percent. When the electric field is reversed and
10 the working electrode acts as the cathode, the device turns black, as can be seen by the low reflectivity of below 30 percent. A wide dynamic range is therefore demonstrated.

In accordance with the present invention, the use of a working electrode in conjunction with a display device as presently disclosed
15 results in extremely fast switching speeds. Speeds of less than 500 milliseconds are typical, with speeds of less than 200 milliseconds being preferred and less than 100 milliseconds being most preferred.

The following examples illustrate various aspects of the present invention and are not intended to limit the scope thereof.

20 Example 1

A working electrode is produced by the following techniques. A gold coating is applied to a polyethylene substrate by sputtering to a thickness of 0.2 micron. The gold is then etched by
25 photolithography to form a 2.54 cm by 2.54 cm (1 inch by 1 inch) square grid having a grid pattern similar to that shown in Figure 2. The grid has line spacings of 500 microns, line widths of 20 microns and line heights of 0.2 micron. A coating of indium tin oxide is then deposited on the grid and substrate by sputtering at room temperature. The indium tin oxide coating has a thickness of

- 16 -

approximately 1000 Angstroms and a sheet resistivity of about 100 ohms per square. An electrolyte is prepared by forming an aqueous solution of 25 percent zinc bromide. Thirty weight percent polyvinyl alcohol is dissolved in the solution. Pigment grade TiO_2 is then
5 mixed into the solution to a concentration of 40 percent by weight. The solution is thoroughly stirred and degassed. A counter electrode is formed from a 2.29 cm by 2.29 cm (0.9 inch by 0.9 inch) glass epox circuit board to which a 25 micron (1 mil) thick sheet of copper has been clad. The electrolyte is sandwiched between the working
10 electrode and counter electrode to a thickness of about 125 microns (5 mils). The edges of the device are sealed with epoxy to provide a seal that maintains the water content in the electrolyte. Electrical contacts are attached to each of the working electrode and counter electrode. A 1.5 volt electric field is applied between the working
15 electrode and counter electrode, with the working electrode serving as the cathode. Within 100 milliseconds of application of the electric field, the device turns black, resulting in a reflectivity in the visible range of less than 30 percent. Reversal of polarity results in bleaching of the device back to a white state within 100
20 milliseconds, resulting in a reflectivity of visible light of greater than 70 percent.

Example 2

Example 1 is repeated with the exception that Cu is used as the metal grid in place of Au and is deposited to a thickness of 3
25 microns. In operation, the device similarly switches from white to black within 100 milliseconds and then upon reversal of the electric field switches from black to white within 100 milliseconds. A dynamic range similar to that of Example 1 is demonstrated.

Example 3

Examples 1 and 2 are repeated with the exception that polytetrafluoroethylene is used as a substrate in place of polyethylene. In operation, switching speeds of the devices are
5 similar to the devices of Examples 1 and 2, i.e., less than 100 milliseconds, and dynamic ranges are comparable.

Example 4

Examples 1 and 2 are repeated with the exception that polyester is used as a substrate in place of polyethylene. In operation,
10 switching speeds of the devices are similar to the devices of Examples 1 and 2, i.e., less than 100 milliseconds, and dynamic ranges are comparable.

Example 5

Examples 1 and 2 are repeated with the exception that soda glass is used as a substrate in place of the polyethylene. In operation,
15 switching speeds of the devices are similar to the devices of Examples 1 and 2, i.e., less than 100 milliseconds, and dynamic ranges are comparable.

Example 6

20 Examples 1 and 2 are repeated with the exception that tin oxide is used as the metal oxide coating in place of the indium tin oxide. In operation, switching speeds of the devices are similar to the devices of Examples 1 and 2, i.e., less than 100 milliseconds, and dynamic ranges are comparable.

Example 7

Examples 1 and 2 are repeated with the exception that zinc iodide is used in the electrolyte in place of zinc bromide. In operation, switching speeds of the devices are similar to the devices of
5 Examples 1 and 2, i.e., less than 100 milliseconds, and dynamic ranges are comparable.

Example 8

Examples 1 and 2 are repeated with the exception that
10 poly-2-acrylamido-2-methylpropane sulfonic acid is used as the polymeric resin in place of the polyvinyl alcohol. In operation, switching speeds of the devices are similar to the devices of Examples 1 and 2, i.e., less than 100 milliseconds, and dynamic ranges are comparable.

Example 9

15 Multiple display devices fabricated as in Example 1, having surface areas of 2.54 cm by 2.54 cm (1 inch by 1 inch), are positioned in 12 rows and 12 columns to form a 30.5 cm by 30.5 (1 foot by 1 foot) surface. Electrical contacts are made to the working electrode and counter electrode of each device. A 1.5 volt electric
20 field is applied simultaneously to each device with the working electrode serving as the cathode. Within 100 milliseconds of application of the electric field, the entire 30.5 cm by 30.5 cm (1 foot by 1 foot) surface turns black. Reversal of polarity results in bleaching of the surface back to a white state within 100
25 milliseconds.

It is to be noted that the above description of the present invention is susceptible to considerable modification, change and adaptation by those skilled in the art, and that such modifications, changes and adaptations are intended to be considered within the
30 scope of the present invention, which is set forth by the appended claims.

We Claim:

1. A working electrode for use in a display device, the working electrode comprising:
 - (a) a metal grid; and
 - 5 (b) a metal oxide coating disposed on the metal grid.
2. A working electrode according to claim 1, wherein the metal grid comprises Cu, Au, Ag, Al, Pt, Ni, Zn and combinations thereof.
3. A working electrode according to claim 1, wherein the metal grid comprises Au.
- 10 4. A working electrode according to claim 1, wherein the metal grid has line widths of from about 5 to about 200 microns, line spacings of from about 100 to about 2000 microns and line heights of from about 0.1 to about 100 microns.
- 15 5. A working electrode according to claim 4, wherein the metal grid has line widths of about 20 microns, line spacings of about 500 microns and line heights of from about 0.2 to about 3 microns.
6. A working electrode according to claim 1, wherein the metal grid has an electrical resistivity of from about 0.02 to about 3 ohms per square.
- 20 7. A working electrode according to claim 6, wherein the metal grid has an electrical resistivity of about 0.4 ohms per square.
8. A working electrode according to claim 1, wherein the metal oxide coating comprises indium oxide, tin oxide, indium tin oxide zinc oxide or cadmium stannate.
- 25 9. A working electrode according to claim 1, wherein the metal oxide coating comprises indium tin oxide.

- 20 -

10. A working electrode according to claim 1, wherein the metal oxide coating has a thickness of from about 50 to about 2000 Angstroms.

11. A working electrode according to claim 1, wherein the metal
5 oxide coating has a thickness of about 1000 microns.

12. A working electrode according to claim 1, wherein the metal oxide coating has an electrical resistivity of from about 10 to about 10,000 ohms per square.

13. A working electrode according to claim 1, wherein the metal
10 oxide coating has an electrical resistivity of from about 100 to about 200 ohms per square.

14. A working electrode according to claim 1, wherein the working electrode further comprises a substrate upon which the metal grid and metal oxide coating are disposed.

15. A working electrode according to claim 14, wherein the
15 substrate comprises a glass selected from soda glass and borosilicate glass.

16. A working electrode according to claim 14, wherein the
20 substrate comprises a polymer selected from polyethylene polytetrafluoroethylene and polyester.

17. A working electrode according to claim 16, wherein the substrate comprises polyethylene.

- 21 -

18. A display device comprising:
- (a) a working electrode comprising a metal grid having a metal oxide coating disposed thereon;
 - (b) a counter electrode; and
 - 5 (c) an electrochromic material disposed between the working electrode and counter electrode wherein the metal oxide coating is disposed between the metal grid and the electrochromic material.
19. A display device according to claim 18, wherein the metal
10 grid comprises Cu, Au, Ag, Al, Pt, Ni, Zn and combinations thereof.
20. A display device according to claim 18, wherein the metal grid comprises Au.
21. A display device according to claim 18, wherein the metal oxide coating comprises indium oxide, tin oxide, indium tin oxide,
15 zinc oxide or cadmium stannate.
22. A display device according to claim 18, wherein the metal oxide coating comprises indium tin oxide.
23. A display device according to claim 18, wherein the working electrode further comprises a substrate upon which the metal grid and
20 metal oxide coating are disposed.
24. A display device according to claim 23, wherein the substrate comprises a glass selected from soda glass and borosilicate glass.
25. A display device according to claim 23, wherein the
25 substrate comprises a polymer selected from polyethylene polytetrafluoroethylene and polyester.
26. A display device according to claim 23, wherein the substrate comprises polyethylene.

- 22 -

27. A display device according to claim 18, wherein the electrochromic material comprises an aqueous solution of an electrodepositable metal.

28. A display device according to claim 27, wherein the
5 electrodepositable metal is Zn, Co, Ni or combinations thereof.

29. A display device according to claim 27, wherein the electrodepositable metal is provided from a metal salt selected from chlorides, bromides, iodides and combinations thereof.

30. A display device according to claim 18, wherein the
10 electrochromic material comprises a polymer selected from polyaniline, polyacetylene, polypyrrole and polythiophene.

31. A display device according to claim 18, wherein the electrochromic material comprises a metal oxide selected from WO_3 , MoO_3 , and Ni(OH)_2 .

32. A display device according to claim 18, wherein the
15 electrochromic material comprises Prussian blue.

33. A display device according to claim 18, wherein the device has a response time of less than about 200 milliseconds.

34. A display device according to claim 33, wherein the device
20 has a surface area of greater than about 1 square inch.

35. A display device according to claim 18, wherein the device is capable of switching from a reflectance of greater than about 70 percent to a reflectance of less than about 30 percent.

1 / 2




FIG. 1




FIG. 2

2/2




FIG. 3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 92/02634

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) * According to International Patent Classification (IPC) or to both National Classification and IPC IPC ⁵ : G 02 F 1/155, G 02 F 1/153																							
II. FIELDS SEARCHED <div style="text-align: center; font-size: small;">Minimum Documentation Searched ⁷</div> <table style="width: 100%; border: none;"> <tr> <td style="width: 30%; border: none;">Classification System </td> <td style="border: none;">Classification Symbols</td> </tr> <tr> <td style="border: none; vertical-align: top;">IPC⁵</td> <td style="border: none; vertical-align: top;">G 02 F 1/00, H 01 M 4/00</td> </tr> </table> <div style="text-align: center; font-size: x-small; margin-top: 5px;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are included in the Fields Searched ⁸</div>			Classification System	Classification Symbols	IPC ⁵	G 02 F 1/00, H 01 M 4/00																	
Classification System	Classification Symbols																						
IPC ⁵	G 02 F 1/00, H 01 M 4/00																						
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹ <table border="1" style="width: 100%; border-collapse: collapse; font-size: x-small;"> <thead> <tr> <th style="width: 10%;">Category ¹⁰</th> <th style="width: 70%;">Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²</th> <th style="width: 20%;">Relevant to Claim No. ¹³</th> </tr> </thead> <tbody> <tr> <td style="text-align: center; vertical-align: top;">X</td> <td style="vertical-align: top;">EP, A, 0 417 624 (PPG INDUSTRIES) 20 March 1991 (20.03.91), see page 3, line 21 - page 5, line 4; page 7, lines 11-30.</td> <td style="vertical-align: top; text-align: center;">1, 2, 14, 18, 19, 23, 30, 31</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td style="vertical-align: top;"></td> <td style="vertical-align: top; text-align: center;">4, 5, 15, 16, 24, 25</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">Y</td> <td style="vertical-align: top; text-align: center;">--</td> <td style="vertical-align: top; text-align: center;">27-29</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">Y</td> <td style="vertical-align: top;">EP, A, 0 300 919 (ALPINE POLYVISION) 25 January 1989 (25.01.89), see page 7, line 52 - page 8, line 25; page 10, line 40 - page 12, line 62 (cited in the application).</td> <td style="vertical-align: top; text-align: center;">27-29</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td style="vertical-align: top; text-align: center;">--</td> <td style="vertical-align: top; text-align: center;">18</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">X</td> <td style="vertical-align: top;">US, A, 4 768 865 (GREENBERG et al.) 06 September 1988 (06.09.88),</td> <td style="vertical-align: top; text-align: center;">1, 2, 14, 18, 19, 23,</td> </tr> </tbody> </table>			Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³	X	EP, A, 0 417 624 (PPG INDUSTRIES) 20 March 1991 (20.03.91), see page 3, line 21 - page 5, line 4; page 7, lines 11-30.	1, 2, 14, 18, 19, 23, 30, 31	A		4, 5, 15, 16, 24, 25	Y	--	27-29	Y	EP, A, 0 300 919 (ALPINE POLYVISION) 25 January 1989 (25.01.89), see page 7, line 52 - page 8, line 25; page 10, line 40 - page 12, line 62 (cited in the application).	27-29	A	--	18	X	US, A, 4 768 865 (GREENBERG et al.) 06 September 1988 (06.09.88),	1, 2, 14, 18, 19, 23,
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³																					
X	EP, A, 0 417 624 (PPG INDUSTRIES) 20 March 1991 (20.03.91), see page 3, line 21 - page 5, line 4; page 7, lines 11-30.	1, 2, 14, 18, 19, 23, 30, 31																					
A		4, 5, 15, 16, 24, 25																					
Y	--	27-29																					
Y	EP, A, 0 300 919 (ALPINE POLYVISION) 25 January 1989 (25.01.89), see page 7, line 52 - page 8, line 25; page 10, line 40 - page 12, line 62 (cited in the application).	27-29																					
A	--	18																					
X	US, A, 4 768 865 (GREENBERG et al.) 06 September 1988 (06.09.88),	1, 2, 14, 18, 19, 23,																					
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>* Special categories of cited documents: ¹⁴</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"G" document member of the same patent family</p> </div> </div>																							
IV. CERTIFICATION <table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none; vertical-align: top;"> <div style="border: 1px solid black; padding: 5px; margin-bottom: 5px;"> Date of the Actual Completion of the International Search <div style="text-align: center;">12 August 1992</div> </div> <div style="border: 1px solid black; padding: 5px;"> International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div> </div> </td> <td style="width: 50%; border: none; vertical-align: top;"> <div style="border: 1px solid black; padding: 5px; margin-bottom: 5px;"> Date of Mailing of this International Search Report <div style="text-align: center;">04 SEP 1992</div> </div> <div style="border: 1px solid black; padding: 5px;"> Signature of Authorized Officer <div style="text-align: center;">GRONAU e.h.</div> </div> </td> </tr> </table>			<div style="border: 1px solid black; padding: 5px; margin-bottom: 5px;"> Date of the Actual Completion of the International Search <div style="text-align: center;">12 August 1992</div> </div> <div style="border: 1px solid black; padding: 5px;"> International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div> </div>	<div style="border: 1px solid black; padding: 5px; margin-bottom: 5px;"> Date of Mailing of this International Search Report <div style="text-align: center;">04 SEP 1992</div> </div> <div style="border: 1px solid black; padding: 5px;"> Signature of Authorized Officer <div style="text-align: center;">GRONAU e.h.</div> </div>																			
<div style="border: 1px solid black; padding: 5px; margin-bottom: 5px;"> Date of the Actual Completion of the International Search <div style="text-align: center;">12 August 1992</div> </div> <div style="border: 1px solid black; padding: 5px;"> International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div> </div>	<div style="border: 1px solid black; padding: 5px; margin-bottom: 5px;"> Date of Mailing of this International Search Report <div style="text-align: center;">04 SEP 1992</div> </div> <div style="border: 1px solid black; padding: 5px;"> Signature of Authorized Officer <div style="text-align: center;">GRONAU e.h.</div> </div>																						

(II. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET))		
Category *	Citation of Document, ** with indication, where appropriate, of the relevant passages	Relevant to Claim No.
	see column 2, line 59 - column 3, line 2; column 4, line 18 - column 6, line 26; claims 8-16, 19, 20 (cited in the application).	31
Y		3, 8,
A		20, 21
		4, 15,
		24, 35
Y	EP, A, 0 028 147 (ASAHI GLASS) 06 May 1981 (06.05.81), see page 3, line 19 - page 6, line 23.	3, 20
A		8, 9,
		16, 21,
		22, 25,
		35
Y	US, A, 4 326 017 (WILL) 20 April 1982 (20.04.82), see column 1, line 1 - column 5, line 61; claims 1-3.	8, 21
X	GB, A, 1 564 264 (IBM) 02 April 1980 (02.04.80), see page 2, line 104 - page 3, line 88.	1, 2,
		14, 18,
		19, 23
A		15, 16,
		24, 25,
		27, 29

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

to the International Search
Report to the International Patent
Application No.

rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US 92/02634 SAE 60176

In diesem Anhang sind die Mitglieder
der Patentfamilien der im obenge-
nannten internationalen Recherchenbericht
angeführten Patentdokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visée ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

In Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
EP 417624		AU A1 60927/90	16-05-91
		AU B2 615622	03-10-91
		CA AA 2024658	14-03-91
		EP A2 417624	20-03-91
		EP A3 417624	03-06-92
		IL A0 95555	30-06-91
		JP A2 3107129	07-05-91
		US A 5066111	19-11-91
		US A 5124832	23-06-92
EP 300919		AU A1 21287/88	01-03-89
		DK A0 1336/89	17-03-89
		DK A 1336/89	10-05-89
		EP A1 300919	25-01-89
		FR A1 2618569	27-01-89
		FR B1 2618569	22-12-89
		JP A2 1044423	16-02-89
		US A 5082355	21-01-92
		WO A1 8901180	09-02-89
US A 4768865	06-09-88	AU A1 17559/88	23-02-89
		AU B2 588507	14-09-89
		BR A 8802785	27-12-88
		CA A1 1288155	27-08-91
		EP A1 294756	14-12-88
		JP A2 1078238	23-03-89
EP 28147		DE C0 3065074	03-11-83
		EP A1 28147	06-05-81
		EP B1 28147	28-09-83
		JP A2 56062229	28-05-81
		US A 4338000	06-07-82
US A 4326017	20-04-82	keine - none - rien	
GB A 1564264	02-04-80	CA A1 1067716	14-10-80
		DE A1 2815062	02-11-78
		DE C2 2815062	22-11-84
		FR A1 2388359	17-11-78
		FR B1 2388359	08-07-83
		JP A2 53129998	13-11-78
		JP B4 62007531	18-02-87
		US A 4167309	11-09-79

THIS PAGE BLANK (USPTO)